



HYROX



TECHNICAL DATA

Edition of: 2010-12-8

Trade name	Iron oxide brown			
Type	655			
REACH	Registration No. 01-2119457614-35-0043, 01-2119457554-33-0014, 01-2119457646-28-0014			
Chemical name	Synthetic iron oxide			
Delivery form	Powder			
Colour index	Combination of Pigment red 101, yellow 42 and black 11			
CAS No./EC No.	1309-37-1, 51274-00-1, 1317-61-9/215-168-2,257-098-5,215-277-5			
Specifications	Contents	%	≥88	ISO1248
	Oil absorption	ml/100g	20~30	ISO787-5
	Res. on 325 mesh	%	≤0.3	ISO787-7
	Water soluble salts	%	≤0.5	ISO787-3
	Moisture	%	≤1.5	ISO787-2
	pH value		4~7	ISO787-9
	Ignition loss (1,000°C, ½ h)	%		DIN55913
	Bulk density	g/cm ³	0.6~0.9	ISO787-11
	Specific gravity	g/cm ³	4.8	ISO787-10
	Particle size BET	µm	Irregular	Electron Micrographs
	Dispersibility (Hegman)	µm		ISO787-20
	Tinting Strength (Compared with Standard)	%	95~105	ISO787-24
	Color Difference ΔE (Compared with Standard)		≤1.0	ISO787-1
	Sales packing	In 25kg paper bag/900kg bulk bag then palletized		
Transport & Storage	Protect against weathering / Store in a dry place, temperatures of above 80 °C must be avoided			
Safety	The product is not classified as hazardous under EC 1907/2006 & EC 1272/2008			



شرکت سهند تجارت کارن
نماینده انحصاری در ایران
WWW.SAHANDTDC.COM

شرکت پودر کربنات زاگروس
عامل بخش انحصاری در ایران
(021) 44 15 8390-92

